

ABSFC-AG15A2 (ABS HIGH GLOSS GENERAL PURPOSE RESIN)

SR NO	Property	Unit	Test Method	Test Condition	DATA
1	TENSILE STRENGTH	Kg/cm ² (MPa)	ASTM D-638 (IS0527)	23°C	470 (46)
2	FLEXURAL STRENGTH	Kg/cm ² (MPa)	ASTM D-790 (IS0178)	23°C	840 (83)
3	FLEXURAL MODULUS	Kg/cm ² (MPa)	ASTM D-790 (IS0178)	23°C	28000 (2750)
4	ROCKWELL HARDNESS	R-Scale	ASTM D-785 (IS02039/2)	23°C	R-108
5	IZOD IMPACT STRENGTH	Kg-cm/cm (J/m)	ASTM D-256 (ISO R180)	23°C 1/4" bar	20 (196)
6	VICAT SOFTENING TEMPERATURE	°C	ASTM D-1525 (IS0306)	1 kg load	104
7	HEAT DEFLECTION TEMPERATURE	°C	ASTM D-648 (ISO 75/A)	Unannealed 18.6kg/cm ² (1/2" bar)	89
				Annealed 18.6kg/cm ² (80°C x 8Hr)	101
8	MELT FLOW INDEX	g/10 min	ASTM D-1238 (IS01133)	200°C x 5Kg (49N)	1.7
				220°C x 10Kg (98N)	19
9	MOLDING SHRINKAGE	%		23°C	0.4~0.7
10	SPECIFIC GRAVITY		ASTM D-792 (IS01183)	23°C/23°C	1.05
11	FLAMMABILITY		UL-94	FILE NO. E162823	1/16" HB ALL COLOR

Characteristics: High gloss · Medium impact grade · High temp. molding ·

Application : Toys, Clock housing, Stereo housing, Suitcase · House wares appliance ·