

\* SPECIFICATIONS FOR PAVING ASPHALT 60/70:

Items	Unit	Limitation		Test Method
		Min	Max	
Penetration	at 25°C	60	70	D5
Flash Point (COC)	°C(°F)	232°C /450°F	-	D92
Ductility	25°C (77°F), 5cm/min, cm	130	-	D113
	15°C, 5cm/min., cm	100	-	D113
Solubility in Trichloroethylene	%	99	-	D2042
Wax Content	% Wt	-	2.0	DIN52015
Softening Point	°C	46	52	D36
Thin-film Oven Test	1/8 in. (3.2mm), 163°C (325°F), 5hr			
Penetration of Residue	% of Original	54	-	D5
Ductility of Residue	25°C (77°F), 5cm/min, cm	100	-	D113
	15°C, 5cm/min., cm	Measured value	-	D113
Loss on Heating	%	-	0.2	D6

Note: 1.\* Based on AASHTO: M20-70(1982)

2. ASTM D1754-83 Thin-Film Oven Test

**Disclaimer:** It makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.