

PRECIPITATED CALCIUM CARBONATE (coated)

Grades	CCFP-200	CCFP-300	CCFP-400D	CCFP-500S	CCFP-202	CCFP-301	CCFP-302	Test Method
Properties								
Appearance	White powder	White powder	Yellowish white powder	White powder	White powder	White powder	White powder	-----
Coating agent	Fatty acid	Fatty acid	Rosin acid	Fatty acid	Fatty acid	Fatty acid	Fatty acid	-----
Specific Surface Area BET (m²/g)	16	24	25	17	12	19	16	BET
Particle Size (μm)	0.10	0.06	0.06	0.08	-----	-----	-----	SEM
Bulk Density (g/cm³)	0.26	0.24	0.25	0.30	0.27	0.30	0.32	JIS K5101
DOP oil absorption (cc/100g)	25	31	31	22	18	24	19	JIS K5101
Whiteness (%)	≥ 96	≥ 95	≥ 90	≥ 96	≥ 96	≥ 96	≥ 96	KETT C-1 TYPE
Moisture (%)	≤ 0.5	≤ 0.6	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5	----- -
PH	8.6	8.8	8.5	8.1	9.0	9.0	9.0	JIS K5101

Disclaimer: It makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.