

COFP Calcium Oxide

Item Properties	Composition (%)			Applications
	CaO	S	P	
Massive 4~65mm	93±3	0.050±0.010	0.012±0.003	Stainless steel mill
Massive 4~65mm	93±3	0.060±0.010	0.012±0.003	Melts the industry Gypsum industry
Massive 4~65mm	93±3	0.060±0.010	0.012±0.003	Generally ironworks
Granular 4~65mm	90±3	0.10±0.020	0.012±0.003	Exsiccator
Granular 4~65mm	90±3	0.10±0.020	0.012±0.003	White lime raw material
Granular 4mm ↓	90±3	0.10±0.020	0.012±0.003	White lime raw material
Graduation powder lime 250mesh 85%	88±3	0.10±0.020	0.012±0.003	Mixes plans earth permeating to become spongy uses Refractory brick material
Description	CaO、S、P test method : JIS R 9011			

Disclaimer: It makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.