INKER 1200

Naphthenic Ink 0il

This severely hydrotreated naphthenic printing ink oil has a low odor level, and good solvency and volatility.

TEST DESCRIPTION		TEST METHOD	SPECIFICATIONS		MARKETING
			Min	Max	VALUES
Physical Properties					
1	Viscosity, SUS at 100°F(37.8℃)	ASTM D 445	1200	1300	1236
2	Viscosity, SUS at 210°F(98.9℃)	ASTM D 445			77.7
3	Viscosity, cSt at 40°C(104°F)	ASTM D 341			228
4	Viscosity,cSt at 100°C(212°F)	ASTM D 341			14.4
5	API Gravity, 60°F(15.6°C)	ASTM D 1250			22. 2
6	Specific Gravity, 60°F(15.6°C)	ASTM D 4052			0. 9206
7	Viscosity- Gravity Constant	ASTM D 2501			0.8527
8	Density, lbs/gal at 60°F	ASTM D 1250			7. 666
9	Molecular Weight	ASTM D 2502			459
10	Flash Point, COC, °F(°C)	ASTM D 92	400(204)		470(243)
11	Color, ASTM	ASTM D 6045		3. 0	L2. 5
12	Pour Point,°F(°C)	ASTM D 5949		25(-4)	-3(-19)
13	Water Content	ERTM-1	PASS		PASS
14	Appearance	ERTM-2	PASS		PASS
	Chemical Properties				
1	Aniline Point,°F(°C)	ASTM D 611	195.0(90.6)	210.0(98.9)	201.7(94.3)
Health and Safety Properties					
1	Polycyclic Aromatic Compounds, wt%	IP 346		3	<3
2	Modified Ames Assay	ASTM E 1687	PASS		PASS

Disclaimer: It makes no warrantees, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.