

MBFP PP-MW-PX4 (PE white master batch)

PP-based white master batch containing highly dispersive TiO₂ and ultra fine calcium carbonate. It applies well in PP injection, extrusion, blow molding, film etc.

| Grades | MBFP PP-MW-PX5 | MBFP PP-MW-PX4 |
|---|-----------------------|-----------------------|
| Properties | | |
| Carrier | PP | |
| TiO₂ content (%) | 55 | 45 |
| CaCO₃ content (%) | 0 | 25 |
| Melt index^(2.16kg/230°C) (g/10mins) | 4.0 | 13.0 |
| Moisture^{*1}(%) | < 0.20 | < 0.20 |
| Opacity^{*2}(%) | 31.50 | 29.50 |

Data shown are average values and should not be examined for specifications.

*¹By IR moisture meter

*²Blown film processing

Materials: MBFP PP-WHITE MASTER BATCH content 4 PHR, base material TAISOX PE#9001

Settings: blown film ratio 3.5~4, thickness 20 μm.

Packing: 25kg paper bag or 500kg jumbo bag.