

MBFP TC-P2 (Masterbatch of CaCO₃+PP)

PROPERTIES		UNIT	MBFP TC-P1	MBFP TC-P2	MBFP TC-E1
Melt Index	2.16kg@190°C	g/10 mins	3-23	3-23	3-23
	5kg@190°C	g/10 mins	-----	-----	-----
	2.16kg@230°C	g/10 mins	-----	-----	-----
Density@23°C		g/cm ³	1.80	1.80	1.90
Moisture		%	< 0.25	< 0.25	< 0.25
CaCO ₃ content		%	80	80	80
Base material		---	PP APP	PP APP	HDPE APP
Applications			Flat yarn Woven bags Strapping bands	Injection, blow and extrusion molding	

Disclaimer: It makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.