# MBFP U-CAL

#### Masterbatch of CaCO<sub>3</sub> + PP

Grade: MBFP UC- MP2

# Applications

- 1. Flat yarn
- 2. Strapping band
- 3. Injection molding, blow molding, extrusion molding

#### **Features**

- 1. MBFP UC-MP2 is a PP-based masterbatch containing 80% ultra-fine calcium carbonate. It is grayish white color with excellent dispersibility.
- 2. It can be mixed with PP resin for extrusion, thermal forming, injection etc. and is easy to disperse with good compatibility. It functions as a modifier to improve the heat resistance, gloss, flexural strength, size stability, printability and texture. It also reduces heat release from burning and therefore prevents further environmental pollution.

### Processing suggestions

- 1. General loading at 5~40 % with variation according to the product.
- 2. The processing temperature is set according to resin's processing temperature, generally at 240±40°C.

# Basic properties

1. MBFP UC-MP2 properties

Properties	Test method	Unit	Typical value
Base material		•••••	PP
CaCO₃ content	•••••	%	80
MI@2.16kg/230°C	ASTM D1238	g/10mins	2. 2
Density@23℃	ASTM D1505	g/cm³	1.9
Moisture	IR moisture meter	%	< 0.20
Shape	•••••	granule	$2 \sim 3$ mm $^{^{\oplus}}$

2. Injection sheet properties of MBFP UC-MP2 mixing with YUNGSOX PP-3080

Properties  MBFP UC-MP2(%)	Tensile strength at break (kg/cm²)	Flexural modulus (kg/cm²)	IZOD Impact strength (kg•cm/cm)
0	. 266	10247	10.2
5	262	10911	8.6
10	260	11958	7. 5
15	255	12747	7. 0
20	243	13812	6. 5
30	225	16562	6. 0

Packing: 25kg/bag