

RPAP N2

(NAPHTHENIC RUBBER PROCESS OIL)

RPAP N2 is a naphthenic rubber processing conforming to ASTM 103 Type, formulated from carefully selected hydrogenated Naphthenic base oils. These are non staining in nature and possess excellent thermal, oxidation and color stability. It is compatible for processing NR, SBR, PBR, EPDM, TPR/TPE Rubber.

Sr No	Characteristics	Unit	Test Method	Guaranteed Data	
				Min	Max
1	Color		ASTM D-1500		3.5
2	Density at 29.5°C	gm/ml	ASTM D-1298	0.85	0.9
3	Kinematic Viscosity at 40°C	cSt	ASTM D-445	90	105
4	Flash Point, COC	°C	ASTM D-92	215	
5	Pour Point	°C	ASTM D-97		-3
6	Aniline Point	°C	ASTM D-611	100	110
8	Neutralization Number	mg KOH/gm	ASTM D-974		0.10

APPLICATIONS: RPAP N2 is suitable for the following applications:

- Manufacturing of Automotive Tubes
- Light coloured non black Foot Wear products
- Molded extended products

Disclaimer: It makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.