

RPER L2000

Product Data Sheet

This severely hydrotreated naphthenic process oil provides good solvency for the rubber and chemical processing industries. It has a low pour point, a low odor level, excellent color, and resistance to discoloration by heat or ultraviolet light.

TEST DESCRIPTION		TEST METHOD	SPECIFICATIONS		MARKETING VALUES
			Min	Max	
Physical Properties					
1	Viscosity, SUS at 100°F(37.8°C)	ASTM D 445	2000	2400	2093
2	Viscosity, SUS at 210°F(98.9°C)	ASTM D 445			101.0
3	Viscosity, cSt at 40°C(104°F)	ASTM D 341			383
4	Viscosity, cSt at 100°C(212°F)	ASTM D 341	19	25	20
5	API Gravity, 60°F(15.6°C)	ASTM D 1250			21.8
6	Specific Gravity, 60°F(15.6°C)	ASTM D 4052			0.9230
7	Viscosity- Gravity Constant	ASTM D 2501			0.8495
8	Density, lbs/gal at 60°F	ASTM D 1250			7.686
9	Molecular Weight	ASTM D 2502			507
10	Flash Point, COC, °F(°C)	ASTM D 92	470(243)		510(266)
11	Color, ASTM	ASTM D 6045		4.0	12.5
12	Pour Point, °F(°C)	ASTM D 5949		30(-1)	7(-14)
13	Volatility, wt%, 225°F (Evap.Loss)	ASTM D 972			0.10
14	Water Content	ERTM-1	PASS		PASS
15	Appearance	ERTM-2	PASS		PASS
16	Glass Transition Temperature (Tg), °C	ASTM D 3418			-54
Chemical Properties					
1	Acid Number, mg KOH/g	ASTM D 664		0.05	0.01
2	Aniline Point, °F(°C)	ASTM D 611	200(93)	215(102)	209(98)
3	Sulfur, wt%	ASTM D 4294			0.085
4	Sulfur, ppm	ASTM D 4294			850
5	Refractive Index, 20°C (68°F)	ASTM D 1218			1.5080
6	UV absorptivity at 260nm	ASTM D 2008			5.79
7	Clay-Gel, wt%	Asphaltenes	ASTM D 2007		<0.1
		Polar Compounds			2.8
		Aromatics			40.0
		Saturates			57.2
8	Carbon Type Analysis, %	Ca	ASTM D 2140		13
		Cn			32
		Cp			55
Health and Safety Properties					
1	Polycyclic Aromatic Compounds, wt%	IP 346		3	< 3
2	Modified Ames Assay	ASTM E 1687	PASS		PASS

Disclaimer: It makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.