

# RPER L200

# Product Data Sheet

This severely hydrotreated naphthenic process oil provides good solvency for the rubber and chemical processing industries. It has a low pour point, a low odor level, excellent color, and resistance to discoloration by heat or ultraviolet light.

TEST DESCRIPTION		TEST METHOD	SPECIFICATIONS		MARKETING VALUES
			Min	Max	
<b>Physical Properties</b>					
1	Viscosity, SUS at 100°F(37.8°C)	ASTM D 445	200	215	209
2	Viscosity, SUS at 210°F(98.9°C)	ASTM D 445			43.5
3	Viscosity, cSt at 40°C(104°F)	ASTM D 341			39.9
4	Viscosity, cSt at 100°C(212°F)	ASTM D 341			5.1
5	API Gravity, 60°F(15.6°C)	ASTM D 1250			23.8
6	Specific Gravity, 60°F(15.6°C)	ASTM D 4052			0.9111
7	Viscosity- Gravity Constant	ASTM D 2501			0.8638
8	Density, lbs/gal at 60°F	ASTM D 1250			7.587
9	Molecular Weight	ASTM D 2502			333
10	Flash Point, COC, °F(°C)	ASTM D 92	340(171)		375(191)
11	Color, ASTM	ASTM D 6045		1.5	L1.0
12	Pour Point, °F(°C)	ASTM D 5949		-10(-23)	-40(-40)
13	Volatility, wt%, 225°F (Evap. Loss)	ASTM D 972			5.70
14	Water Content	ERTM-1	PASS		PASS
15	Appearance	ERTM-2	PASS		PASS
<b>Chemical Properties</b>					
1	Acid Number, mg KOH/g	ASTM D 664		0.05	0.01
2	Aniline Point, °F(°C)	ASTM D 611	170.0(76.7)	190.0(87.8)	177.0(80.6)
3	Sulfur, wt%	ASTM D 4294			0.041
4	Sulfur, ppm	ASTM D 4294			410
5	Refractive Index, 20°C (68°F)	ASTM D 1218			1.4988
6	UV absorptivity at 260nm	ASTM D 2008			2.73
7	Clay-Gel, wt%	Asphaltenes	ASTM D 2007		<0.1
		Polar Compounds			0.8
		Aromatics			37.3
		Saturates			62.0
8	Carbon Type Analysis, %	Ca	ASTM D 2140		12
		Cn			42
		Cp			46
<b>Health and Safety Properties</b>					
1	Polycyclic Aromatic Compounds, wt%	IP 346		3	< 3
2	Modified Ames Assay	ASTM E 1687	PASS		PASS

**Disclaimer:** It makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.