



SFSS-CD-130

De-Aroma Solvent

Test Item	Unit	Specification	Test Results	Test Method
Appearance	-	Clear	Clear	Visual
Specific Gravity, at 15°C	g/cm ³	0.830 ± 0.02	0.8344	ASTM D 4052
Distillation IBP	°C	Min 275	277.4	ASTM D 86
5%		-	282.3	
10%		-	285.3	
50%		-	287.1	
90%		-	291.7	
95%		-	295.0	
FBP		Max 320	304.0	
Flash Point (P-M)	°C	Min 130	142	ASTM D 93
Aniline Point	°C	Min 70	86.8	ASTM D 611
Sulfur Content	mg/kg	Max 3	0.00	ASTM D 5453
Saybolt Color	-	Min 26	+30	ASTM D 156
Refractive Index (N _D 20)	-	-	1.4572	ASTM D 1218
Brome Index (BI)	mgBr ₂ /100g	-	0	ASTM D 2710
Water Content	μg/g	-	37	ASTM D 1744
Corrosion Copper Strip (3hr/50°C)	-	Max 1	1a	ASTM D 130
Kinematic Viscosity	mm ² /s, 40°C	Min 3.5	4.217	ASTM D 445
Aromatic Content	Wt%	Max 0.5	0.06	UOP495

- Low-viscosity base with excellent oxidation stability. Environment-friendly products that can be used to open spaced work area.
- Ink, Metal working oil, PVC viscosity modifier, Sealants, Anti-rust oil, Etc.

Disclaimer: It makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.