

## Product Data Sheet

# TOAP 1020-60UT

TOAP 1020-60UT is a Trace Inhibited Transformer Oil meeting the IEC 60296- 2003- 11, 3<sup>rd</sup> Edition Standard Specification. It also meets the ASTM D 1275 B Test requirement for Corrosive Sulphur.

Sr No	Characteristics	Unit	Test Method	Guaranteed Data		
				Min	Max	
1	Appearance		Visual inspection of oil sample in transmitted light under a thickness of 10 cm at ambient temperature	Clear free from sediment and suspended matter		
2	Density at 20°C	Kg/dm <sup>3</sup>	ISO 3675 or IEC 12185		0.895	
3	Kinematic Viscosity at 40°C	mm <sup>2</sup> /sec	ISO 3104		12	
	at -30°C				1800	
4	Flash Point, PMCC	°C	ISO 2719	135		
5	Pour Point	°C	ISO 3016		-40	
6	Inter Facial Tension at 25°C	mN/m	ISO 6295 (Where it is used as general requirement)	No General Requirement 40 min		
7	Acidity	mg KOH/gm	IEC 62021-1		0.01	
8	Water Content, Bulk/Drum	mg/kg	IEC 60814		30/40	
9	Breakdown Voltage AS Delivered/After Treatment	kV	IEC 60156			
				30/70		
10	Dielectric Dissipation Factor (Tanδ) 90°C & 40 to 60 Hz		IEC 60247 or IEC 61620		0.005	
11	Corrosive Sulphur			No General Requirement		
	Silver Strip, 100°C, 18Hrs Copper Strip, 150°C, 48Hrs		DIN 51353 ASTM D 1275 B	Non Corrosive Non Corrosive		
12	Total Sulphur Content	%	BS 2000 Part 373 or ISO 14596	No General Requirement		
13	Anti Oxidant Addictives	%	IEC 60666	(T) Trace inhibited Oil- 0.08 max		
14	Oxidation Stability		IEC 61125 Method C			
	at 120°C, 332 Hrs	Total Acidity		mg KOH/gm		1.2
		Sludge		%		
	DDF at 90°C		IEC 60247		0.500	
15	Gassing Tendency	μL/min	IEC 60628- A	No General Requirement		
16	PCA content	%	BS 2000 Part 346		3	
17	PCB content	mg/kg	IEC 61619	Not Detectable		
18	2- Furfural Content	mg/kg	IEC 61198		0.1	

**Disclaimer:** It makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.